

PUTTY LV PTE 0530 Polyester Spatula Applied Putty with Short Curing Time For filling of metallic surfaces, car bodies, for leveling of small **Usage** unevenness on metal surface. Perfectly de-rusted and degreased surfaces; **Substrate** Old coats cleaned and degreased; Surfaces finished with anticorrosion paints Akrylmetal LV PL, LV AKZ, LV EPS or with alkyd, epoxy, water-based paints. When applied to freshly zinc-plated sheet metal, the surface should first be pre-treated with a reactive paint (such as S 2008). **Initiator LV BP 200 Hardening** component min. 5 min at 20 °C Pot life of mixed coating All types of common paints **Topcoats** initiator putty Mixing ratio 100 weight parts: 1.5 - 2.0 weight parts Thinners C 6000, B 6000 **Cleaning of tools** Clean spatula **Application** 30 minutes at 20 °C Curing time to dry-tosand Wet abrasive paper no. 120 - 240Sanding Dry abrasive paper no. 100 - 220 When handling the product follow all safety precautions indicated in the Material Safety Data Sheet and the label. Caution Flammable liquid, Hazard Class II. Contains organic solvents. Store in a dry place at temperatures from 10 °C to 25 °C.

SYNPO, akciová společnost

S. K. Neumanna 1316, 532 07 Pardubice, Czech Republic

Tel: +420466 067 250 Fax: +420 466 304 644

e-mail: akrylmetal@synpo.cz

Valid from December 2014